

# GOVERNMENT OF INDIA MINISTRY OF SKILL DEVELOPMENT & ENTREPRENEURSHIP DIRECTORATE GENERAL OF TRAINING

### **COMPETENCY BASED CURRICULUM**

## **WELDER**

(Duration: One Year) Revised in July 2022

## CRAFTSMEN TRAINING SCHEME (CTS) NSQF LEVEL- 3



## **SECTOR – CAPITAL GOODS AND MANUFACTURING**





(Engineering Trade)

(Revised in July 2022)

Version: 2.0

## **CRAFTSMEN TRAINING SCHEME (CTS)**

**NSQF LEVEL - 3** 

**Developed By** 

Ministry of Skill Development and Entrepreneurship

**Directorate General of Training** 

### **CENTRAL STAFF TRAINING AND RESEARCH INSTITUTE**

EN-81, Sector-V, Salt Lake City, Kolkata – 700 091 www.cstaricalcutta.gov.in

## **CONTENTS**

SNo.	Topics	Page No.
1.	Course Information	1
2.	Training System	3
3.	Job Role	7
4.	General Information	10
5.	Learning Outcome	12
6.	Assessment Criteria	14
7.	Trade Syllabus	19
8.	Annexure I (List of Trade Tools & Equipment)	31





During the one year duration a candidate is trained on subjects Professional Skill, Professional Knowledge and Employability Skills related to job role. In addition to this a candidate is entrusted to undertake project work and extracurricular activities to build up confidence. The broad components covered under Professional Skill subject are as below:

The practical skills are imparted in simple to complex manner & simultaneously theory subject is taught in the same fashion to apply cognitive knowledge while executing task. The safety aspects covers components like OSH&E, PPE, Fire extinguisher, First Aid and in addition 5S being taught. The practical part starts with edge preparation by hacksawing, filing and fitting followed by Oxy Acetylene Welding & Brazing, Oxy Acetylene Cutting, Shielded Metal Arc Welding, Gas Metal Arc Welding, Gas Tungsten Arc Welding and Spot Welding, Plasma Cutting and Arc Gouging. These processes are widely used in Industries.

During the practice on Welding / Brazing process, the trainees will learn to read the job drawing, select the required base metal and filler metals, cut the metals by appropriate process, carry out edge preparation, setup the plant and do welding/Brazing on M.S, SS, Aluminium and Copper in different positions. On completion of each job the trainees will also evaluate their jobs by visual inspection, and identify the defects for further correction/improvement. They learn to adapt precautionary measures such as preheating; maintaining inter-pass temperature and post weld heat treatment for Welding Alloy steel, Cast Iron etc. The Work Shop calculation taught will help them to plan and cut the required jobs economically without wasting the material and also used in estimating the Electrodes, filler metals etc. The Workshop Science taught will help them to understand the materials and properties, effect of alloying elements etc. Engineering Drawing taught will be applied while reading the job drawings and will be useful in understanding the location, type and size of weld to be carried out.

The professional knowledge taught will be useful in understanding the principles of Welding, Brazing, induction and Cutting process, use of jigs and Fixtures, distortion and methods of control, selection of consumables and to take precautionary measures for storage and handling and apply the same for executing the Cutting, induction Welding, welding and Brazing.

The knowledge and practice imparted on Destructive and Non-destructive testing will be use in understanding the standard quality of welds and to carry out shop floor Inspection and test in laboratories.



One project need to be completed by the candidates in a group. In addition to above components the core skills components viz., Workshop calculation & science, Engineering drawing, employability skills are also covered. These core skills are essential skills which are necessary to perform the job in any given situation.



#### 2.1 GENERAL

The Directorate General of Training (DGT) under Ministry of Skill Development & Entrepreneurship offers a range of vocational training courses catering to the need of different sectors of economy/ Labour market. The vocational training programmes are delivered under the aegis of Directorate General of Training (DGT). Craftsman Training Scheme (CTS) with variantsand Apprenticeship Training Scheme (ATS) are two pioneer schemes of DGT for strengthening vocational training.

Welder trade under CTS is one of the most popular courses delivered nationwide through a network of ITIs. The course is of one-year duration. It mainly consists of Domain area and Core area. In the Domain area (Trade Theory & Practical) imparts professional skills and knowledge, while the core area (Employability Skill) imparts requisite core skills, knowledge, and life skills. After passing out the training program, the trainee is awarded National Trade Certificate (NTC) by DGT which is recognized worldwide.

#### Trainee broadly needs to demonstrate that they are able to:

- Read & interpret technical parameters/documentation, plan and organize work processes, identify necessary materials and tools;
- Perform tasks with due consideration to safety rules, accident prevention regulations and environmental protection stipulations;
- Apply professional knowledge, core skills & employability skills while performing the job, and repair & maintenance work.
- Check the job/ assembly as per drawing for functioning identify and rectify errors in job/ assembly.
- Document the technical parameters in tabulation sheet related to the task undertaken.

#### 2.2 PROGRESSION PATHWAYS

- Can join industry as Technician and will progress further as Senior Technician, Supervisor and can rise up to the level of Manager.
- Can become Entrepreneur in the related field.
- Can join Apprenticeship programme in different types of industries leading to National Apprenticeship certificate (NAC).
- Can join Crafts Instructor Training Scheme (CITS) in the trade for becoming instructor in ITIs.



• Can join Advanced Diploma (Vocational) courses under DGT as applicable.

#### **2.3 COURSE STRUCTURE:**

Table below depicts the distribution of training hours across various course elements during a period of one year: -

S No.	Course Element	Notional Training Hours
1	Professional Skill (Trade Practical)	840
2	Professional Knowledge (Trade Theory)	240
5	Employability Skills	120
	Total	1200

Every year 150 hours of mandatory OJT (On the Job Training) at nearby industry, wherever not available then group project is mandatory.

On the Job Training (OJT)/ Group Project	150

Trainees of one-year or two-year trade can also opt for optional courses of up to 240 hours in each year for 10th/ 12th class certificate along with ITI certification, or, add on short term courses

#### 2.4 ASSESSMENT & CERTIFICATION

The trainee will be tested for his skill, knowledge and attitude during the period of course through formative assessment and at the end of the training programme through summative assessment as notified by the DGT from time to time.

- a) The **Continuous Assessment** (Internal)during the period of training will be done by **Formative assessment method** by testing for assessment criteria listed against learning outcomes. The training institute have to maintain individual *trainee portfolio* as detailed in assessment guideline. The marks of internal assessment will be as per the formative assessment template provided on www.bharatskills.gov.in
- b) The final assessment will be in the form of summative assessment. The All India Trade Test for awarding NTC will be conducted by Controller of examinations, DGT as per the guidelines. The pattern and marking structure is being notified by DGTfrom time to time. **The learning outcome and assessment criteria will be basis for setting question papers for final assessment. The**



**examiner during final examination will also check** individual trainee's profile as detailed in assessment guideline before giving marks for practical examination.

#### 2.4.1 PASS REGULATION

For the purposes of determining the overall result, weightage of 100% is applied for six months and one year duration courses and 50% weightage is applied to each examination for two years courses. The minimum pass percent for Trade Practical and Formative assessment is 60% & for all other subjects is 33%.

#### 2.4.2 ASSESSMENT GUIDELINE

Appropriate arrangements should be made to ensure that there will be no artificial barriers to assessment. The nature of special needs should be taken into account while undertaking assessment. Due consideration should be given while assessing for team work, avoidance/reduction of scrap/wastage and disposal of scarp/wastage as per procedure, behavioral attitude, sensitivity to environment and regularity in training. The sensitivity towards OSHE and self-learning attitude are to be considered while assessing competency.

Assessment will be evidence based comprising some of the following:

- Job carried out in labs/workshop
- Record book/ daily diary
- Answer sheet of assessment
- Viva-voce
- Progress chart
- Attendance and punctuality
- Assignment
- Project work
- Computer based multiple choice question examination
- Practical Examination

Evidences and records of internal (Formative) assessments are to be preserved until forthcoming examination for audit and verification by examination body. The following marking pattern to be adopted for formative assessment:



Performance Level	Evidence
(a) Marks in the range of 60 -75% to be allotted	d during assessment
For performance in this grade, the candidate should produce work which demonstrates attainment of an acceptable standard of craftsmanship with occasional guidance, and due regard for safety procedures and practices.	<ul> <li>Demonstration of good skill in the use of hand tools, machine tools and workshop equipment</li> <li>60-70% accuracy achieved while undertaking different work with those demanded by the component/job/set standards.</li> <li>A fairly good level of neatness and consistency in the finish</li> <li>Occasional support in completing the project/job.</li> </ul>
(b) Marks in the range of above 75% - 90% to b	oe allotted during assessment
For this grade, a candidate should produce work which demonstrates attainment of a reasonable standard of craftsmanship, with little guidance, and regard for safety procedures and practices.	<ul> <li>Good skill levels in the use of hand tools, machine tools and workshop equipment</li> <li>70-80% accuracy achieved while undertaking different work with those demanded by the component/job.</li> <li>A good level of neatness and consistency in the finish</li> <li>Little support in completing the project/job</li> </ul>
(c) Marks in the range of above 90% to be allo	tted during assessment
For performance in this grade, the candidate, with minimal or no support in organization and execution and with due regard for safety procedures and practices, has produced work which demonstrates attainment of a high standard of craftsmanship.	<ul> <li>High skill levels in the use of hand tools, machine tools and workshop equipment</li> <li>Above 80% accuracy achieved while undertaking different work with those demanded by the component/job/set standards.</li> <li>A high level of neatness and consistency in the finish.</li> <li>Minimal or no support in completing the project.</li> </ul>



Welder, Gas; fuses metal parts together using welding rod and oxygen acetylene flame. Examines parts to be welded, cleans portion to be joined, holds them together by some suitable device and if necessary, makes narrow groove to direct flow of molten metal to strengthen joint. Selects correct type and size of welding rod, nozzle etc. and tests welding, torch. Wears dark glasses and other protective devices while welding. Releases and regulates valves of oxygen and acetylene cylinders to control their flow into torch. Ignites torch and regulates flame gradually. Guides flame along joint and heat it to melting point, simultaneously melting welding rod and spreading molten metal along joint shape, size etc. and rectifies defects if any.

Welder, Electric; fuses metals using arc-welding power source and electrodes. Examines parts to be welded, cleans them and sets joints together with clamps or any other suitable device. Starts welding power source and regulates current according to material and thickness of welding. Connect one lead to part to be welded, selects required type of electrode and clamps other lead to electrode holder. May join parts first at various points for holding at specified angles, shape, form and dimension by tack welding. Establish arc between electrode and joint and maintain it throughout the length of the joint.

Welder, Resistance; sets up and operates resistance welding machine to join metal parts, according to blueprints, work orders, or oral instructions. Turns machine dials to set air and hydraulic pressure, amperage, and joining time, according to specified type of metal, weld, and assembly. May select, install, and adjust electrodes. Aligns work pieces, using square and rule. May hold pieces together manually, fasten into jigs, or secure with clamps to align in specified assembly position. Holds part between electrodes or positions on machine worktable. Depresses pedal or pulls trigger to close electrodes and form weld at point of contact. Releases pedal or trigger after specified welding time. Cleans electrodes, using file, tip dresser, emery cloth. May operate machine which automatically releases electrodes from metal after welding cycle. May devise and build fixtures to hold pieces. May inspect finished work. May operate machine equipped with two or more electrodes which weld at several points simultaneously. Important variations include types of joints welded (seam, spot, butt) and types of materials welded (aluminium, steel).

**Gas Cutting**;cuts metal to require shape and size by gas flame either manually or by machine. Examines material to be cut and marks it according to instruction of specification. Makes necessary connections and fits required size of nozzle in welding torch. Releases and regulates flow of gas in nozzle, ignites and adjusts flame. Guides flame by hand or machine along cutting line at required speed and cuts metal to required size.



**Brazer;** joints metal parts by heating using flux and filler rods. Cleans and fastens parts to be joined face to face by wire brush. Apply flux on the joint and heats by torch to melt filler rods into joint. Allows it to cool down. Clean and examines the joint.welding or joining two or more metals together using resistive heat caused by changing electromagnetic fields. Check for induction welded joints.

Tungsten Inert Gas (TIG) welder; reads fabrication drawing, examines parts to be welded, cleans them and sets joints with clamps or any other suitable device. Selects suitable tungsten electrode, grinds the edges and fit in to the GTA welding torch. Selects gas nozzle and fit in to the GTA welding torch. Selects suitable filler rods and cleans them. Connects work piece with earth cable, Connects the machine with Inert gas Cylinder, regulator and flow meter. Starts the Constant current GTA welding machine, sets suitable welding current & polarity and inert gas flow. Establish arc through across a column of highly ionized inert gas between work piece and Tungsten electrode. Melts the metal and deposit weld beads on metal surfaces by passing the suitable filler rod in to the weld puddle. Joins metal pieces such as Steel, Stainless steel and Aluminium metals.

Gas Metal Arc Welder/ Metal Inert Gas/ Metal Active Gas/ Gas Metal Welder (MIG/MAG/GMAW); reads fabrication drawing, examines parts to be welded, cleans them and sets joints with clamps or any other suitable device. Connects work piece with earth cable. Connects the machine with suitable gas Cylinder, regulator and flow meter. Connects pre-heater when CO<sub>2</sub> is used as shielding gas. Selects suitable wire electrode, feed it to welding GMA Welding torch through wire feeder. Selects contact tip gas nozzle and fit in to the GMA welding torch. Preheats joints as required. Starts the Constant Voltage GMA welding machine, sets suitable welding voltage & wire feed speed and shielding gas flow, produces arc between work piece and continuously fed wire electrode. Melts the metal and deposit weld beads on the surface of metals or joins metal pieces such as Steel, and Stainless-steel metals.

**Plastic welder;** create joint between two thermoplastics by following the steps to any weld; pressing, heating and cooling.

**Iron and Steel Plasma Cutter-Manual;** cuts different materials (mild carbon steel, stainless steel, aluminium, high tensile and special steels, and other materials) in various profiles. This involve setting-up and preparing operations interpreting the right information from the specification documents, obtaining the right consumables and other materials, etc.

Plan and organize assigned work and detect & resolve issues during execution in his own work area within defined limit. Demonstrate possible solutions and agree tasks within the team.



Communicate with required clarity and understand technical English. Sensitiveto environment, self-learning and productivity.

#### **Reference NCO 2015:**

- (i) 7212.0100 Welder, Gas
- (ii) 7212.0200 Welder, Electric
- (iii) 7212.0700 Welder, Resistance
- (iv) 7212.0400 Gas Cutter
- (v) 7212.0500 –Brazer
- (vi) 7212.0105 Tungsten Inert Gas Welder
- (vii) 7212.0303 Gas Metal Arc Welder/Metal Inert Gas/Metal Active Gas/Gas Metal Welder (MIG/MAG/GMAW)
- (viii) 7212.0111- Repair Welder
- (ix) 7212.0402- Plasma Cutter Manual

#### **Reference NOS:**

- i) CSC/N0204
- ii) CSC/N0201
- iii) CSC/N0209
- iv) CSC/N0212
- v) CSC/N0207
- vi) CSC/N0206
- vii) CSC/N9410
- viii)CSC/N9411
- ix) CSC/N9412
- x) CSC/N9401
- xi) CSC/N9402



## 4. GENERAL INFORMATION

Name of the Trade	Welder		
Trade Code	DGT/1004		
NCO - 2015	7212.0100, 7212.0200, 7212.0700,7212.0400, 7212.0500, 7212.0105, 7212.0303, 7212.0111, 7212.0402		
NOS Covered	CSC/N0204, CSC/N0201, CSC/N0209, CSC/N0212, CSC/N0207, CSC/N0206, CSC/N9410, CSC/N9411, CSC/N9412, CSC/N9401, CSC/N9402		
NSQF Level	Level – 3		
Duration of Craftsmen Training	One year (1200 Hours + 150 hours OJT/Group Project)		
Entry Qualification	Passed 8 <sup>th</sup> class examination		
Minimum Age	14 years as on first day of academic session.		
Eligibility for PwD	LD, LC, DW, AA, DEAF, HH		
Unit Strength (No. Of Student)	20 (There is no separate provision of supernumerary seats)		
Space Norms	100 Sq. m		
Power Norms 16 KW			
Instructors Qualification	for		
1. Welder Trade	B.Voc/Degree in Mechanical/ Metallurgy/ Production Engineering/ Mechatronics from AICTE /UGC recognized university/ college with one year experience in relevant field.  OR  03 yearsDiploma in Mechanical and allied from AICTE/ recognized technical board of education or relevant Advanced Diploma (Vocational) from DGT with two years experience in relevant field.  OR  NTC/NACpassed in the Trade of "Welder" with three years' experience in the relevant field.  Essential Qualification: Relevant Regular / RPL variants of National Craft Instructor Certificate (NCIC) under DGT.		
	Note: Out of two Instructors required for the unit of 2(1+1), one must have Degree/Diploma and other must have NTC/NAC qualifications. However, both of them must possess NCIC in any of its variants.		
2. Workshop Calculation & Science	B.Voc/Degree in Engineering from AICTE/UGC recognized Engineering College/ university with one-year experience in the		



	relevant field.		
	OR		
	03 years Diploma in Engineering from AICTE / recognized board of technical education or relevant Advanced Diploma (Vocational) from DGT with two years' experience in the relevant field.  OR		
	NTC/ NAC in any one of the engineering trades with three years' experience.		
	Essential Qualification:  Regular / RPL variants of National Craft Instructor Certificate (NCIC) in relevant trade		
	OR		
	Regular / RPL variants NCIC in RoDA or any of its variants under DGT		
3. Engineering Drawing	B.Voc/Degree in Engineering from AICTE/UGC recognized Engineering College/ university with one-year experience in the relevant field.		
	OR		
	03 years Diploma in Engineering from AICTE / recognized board of technical education or relevant Advanced Diploma (Vocational) from DGT with two years' experience in the relevant field.  OR		
	NTC/ NAC in any one of the Mechanical group (Gr-I) trades categorized under Engg. Drawing'/ D'man Mechanical / D'man Civil' with three years' experience.		
	Facential Qualification.		
	Essential Qualification:  Regular / RPL variants of National Craft Instructor Certificate (NCIC) in relevant trade		
	OR		
	Regular / RPL variants of NCIC in RoDA / D'man (Mech /civil) or any of its variants under DGT.		
4. Employability Skill	MBA/ BBA / Any Graduate/ Diploma in any discipline with Two		
	years' experience with short term ToT Course in Employability Skills.		
	(Must have studied English/ Communication Skills and Basic		
	Computer at 12th / Diploma level and above)  OR		
	Existing Social Studies Instructors in ITIs with short term ToT Course in Employability Skills.		
5. Minimum Age for	21 Years		
Instructor			
List of Tools and	As per Annexure – I		
Equipment	AS PET ATTICABLE T		



Learning outcomes are a reflection of total competencies of a trainee and assessment will be carried out as per the assessment criteria.

#### **5.1LEARNING OUTCOMES (TRADE SPECIFIC)**

- 1. Set the gas welding plant and join MS sheet in different positionfollowing safety precautions. [Different position: 1F, 2F, 3F, 1G, 2G, 3G.] (NOS: CSC/N0204)
- 2. Set the SMAW machine and perform different type of joints on MS in different position observing standard procedure. [different types of joints- Fillet ( T-joint, lap & Corner), Butt (Square & V); different position 1F, 2F, 3F,4F, 1G, 2G, 3G, 4G] (NOS: CSC/N0204)
- 3. Set the oxy- acetylene cutting plant and perform different cutting operations on MS plate. [Different cutting operation Straight, Bevel, circular] (NOS: CSC/NO201)
- 4. Perform welding in different types of MS pipe joints by Gas welding (OAW). [Different types of MS pipe joints Butt, Elbow, T-joint, angle (45°) joint, flange joint] (NOS: CSC/NO204)
- 5. Set the SMAW machine and perform welding in different types of MS pipe joints by SMAW. [Different types of MS pipe joints Butt, Elbow, T-joint, angle (45°) joint, flange joint] (NOS: CSC/N0204)
- 6. Choose appropriate welding process and perform joining of different types of metals and check its correctness. [appropriate welding process OAW, SMAW; Different metal SS, CI, Brass, Aluminium] (NOS: CSC/N0204)
- 7. Demonstrate arc gouging operation to rectify the weld joints. (NOS: CSC/N0204)
- 8. Test welded joints by different methods of testing. [different methods of testing- Dye penetration test, Magnetic particle test, Nick break test, Free band test, Fillet fracture test] (NOS: CSC/N0204)
- 9. Set GMAW machine and perform welding in different types of joints on MS sheet/plate by GMAW in various positions by dip mode of metal transfer. [different types of joints-Fillet (T-joint, lap, Corner), Butt (Square & V); various positions- 1F, 2F, 3F,4F, 1G, 2G, 3G] (NOS: CSC/NO209)
- 10. Set the GTAW machine and perform welding by GTAW in different types of joints on different metals in different position and check correctness of the weld. [different types of joints- Fillet ( T-joint, lap, Corner), Butt (Square & V); different metals- Aluminium, Stainless Steel; different position- 1F & 1G] (NOS: CSC/NO212)
- 11. Perform Aluminium & MS pipe joint by GTAW in flat position. (NOS: CSC/N0212)
- 12. Set the Plasma Arc cutting machine and cut ferrous & non-ferrous metals. (NOS: CSC/NO207)
- 13. Set the resistance spot welding machine and join MS& SS sheet. (NOS: CSC/N0206)



- 14. Perform joining of different similar and dissimilar metals by brazing operation as per standard procedure. [different similar and dissimilar metals- Copper, MS, SS] CSC/N9410
- 15. Repair Cast Iron machine parts by selecting appropriate welding process. [Appropriate welding process- OAW, SMAW] CSC/N9411
- 16. Hard facing of alloy steel components/ MS rod by using hard facing electrode. CSC/N9412
- 17. Read and apply engineering drawing for different application in the field of work. CSC/N9401
- 18. Demonstrate basic mathematical concept and principles to perform practical operations. Understand and explain basic science in the field of study. CSC/N9402



	LEARNINGOUTCOMES	ASSESSMENT CRITERIA	
1.	Set the gas welding plant and join MS sheet in different positionfollowing safety precautions.  [Different position: - 1F, 2F, 3F, 1G, 2G, 3G.] (NOS: CSC/N0204)	flame, filler rod as per requirement.  Prepare, set and tack the pieces as per drawing.  Set up the tacked joint in specific position.	
2.	Set the SMAW machine and perform different type of joints on MS in different position observing standard procedure. [different types of joints- Fillet ( T-joint, lap & Corner), Butt (Square & V); different position - 1F, 2F, 3F,4F, 1G, 2G, 3G, 4G] (NOS: CSC/N0204)	Plan and select the type & size of electrode, welding current.  Prepare edge as per requirement  Prepare, set SMAW machine and tack the pieces as per drawing.  Set up the tacked pieces in specific position.  Deposit the weld maintaining appropriate arc length, electrode angle, welding speed, weaving technique and safety aspects.  Clean the welded joint thoroughly.  Carry out visual inspection for appropriate weld joint & check by gauges.	
3.	Set the oxy- acetylene cutting plant and perform different cutting operations on MS plate. [Different cutting operation – Straight, Bevel, circular] (NOS: CSC/NO201)	Plan and mark on MS plate surface for straight/bevel/circular cutting.  Select the nozzle size and working pressure of gases as per requirement.  Set the marked plate properly on cutting table.  Set the cutting plant & perform the cutting operation maintaining proper techniques and all safety aspects.  Clean the cutting burrs and inspect the cut surface for soundness of cutting.	
4.	Perform welding in different types of MS pipe joints by Gas welding (OAW). [Different types of MS pipe joints – Butt, Elbow, T-joint, angle (45°) joint, flange joint] (NOS: CSC/NO204)	Plan and prepare the development for a specific type of pipe joint.  Mark and cut the MS pipe as per development.  Select the size of filler rod, size of nozzle, working pressure etc.  Set and tack the pieces as per drawing.  Deposit the weld bead maintaining proper technique and safety aspects.	



		Inspect the welded joint visually for poor penetration, uniformity of bead and surface defects.
5. Set the SMAW machine and perform welding in different		Plan and prepare the development for a specific type of pipe joint.
	types of MS pipe joints by	Mark and cut the MS pipe as per development.
	SMAW. [Different types of	Select the electrode size and welding current for welding.
	MS pipe joints – Butt,	Set and tack the pieces as per drawing.
	Elbow, T-joint, angle (45°) joint, flange joint]	Deposit the weld bead maintaining proper technique and safety aspects.
	(NOS: CSC/N0204)	Insect the welded joint visually for root penetration, uniformity of bead and surface defects.
6.	Choose appropriate welding	Plan and prepare the pieces for welding.
J.	process and perform joining	Select the type and size of filler rod and flux/electrode,
	of different types of metals	size of nozzle and gas pressure/welding current,
	and check its correctness.	preheating method and temperature as per requirement.
	[appropriate welding	Set and tack metals as per drawing.
	process – OAW, SMAW;	Deposit the weld maintaining appropriate technique and
	Different metal – SS, CI,	safety aspects.
	Brass, Aluminium]	Cool the welded joint by observing appropriate cooling
	(NOS: CSC/N0204)	method. Use post heating, peening etc. as per
		requirement.
		Clean the joint and inspect the weld for its uniformity and
		different types of surface defects.
7.	Demonstrate arc gouging	Plan and select the size of electrode for Arc gouging.
	operation to rectify the	Select the polarity and current as per requirement.
	weld joints. (NOS:	Perform gouging adapting proper gouging technique.
	CSC/N0204)	Clean and check to ascertain the required stock removed.
8.	Test welded joints by	Plan and select the job and clean the surface thoroughly.
	different methods of	Select the appropriate testing methods.
	testing. [different methods	Perform testing of welded joints adapting standard
	of testing- Dye penetration	operating procedure.
	test, Magnetic particle test,	Record the test result & compare with standard
	Nick break test, Free band	parameter/ result value.
	test, Fillet fracture test] (NOS: CSC/N0204)	Accept/reject the job based on test result.
9.	Set GMAW machine and	Select size of electrode wire, welding voltage, gas flow
	perform welding in different	rate, wire feed rate as per requirement.
	types of joints on MS	Prepare, set (machine & Job) and tack the pieces as per
		•



1 ./ 1		
sheet/plate by GMAW in	drawing and type of joints.	
various positions by dip	Set up the tacked joint in specific position.	
mode of metal transfer.	Deposit the weld adapting proper welding technique and	
[different types of joints-	safety aspects.	
Fillet ( T-joint, lap, Corner),	Carry out visual inspection to ensure quality of welded	
Butt (Square & V); various	joint.	
positions- 1F, 2F, 3F,4F, 1G,	Inspect the weld using Dye-penetration Test	
2G, 3G]	(DPT)/Magnetic particle Test (MPT).	
(NOS: CSC/N0209)	(ST 1), Wagnetic particle rest (Wil 1).	
10. Set the GTAW machine and	Select power source as per material, size and type of	
perform welding by GTAW	Tungsten electrode, welding current, gas nozzle size, gas	
in different types of joints	flow rate and filler rod size as per requirement.	
	·	
	Prepare, set (machine & Job) and tack the pieces as per	
different position and check	drawing and type of joints.	
correctness of the weld.	Set up the tacked joint in specific position.	
[different types of joints-	Deposit the weld by adapting proper welding technique	
Fillet ( T-joint, lap, Corner),	and safety aspects.	
Butt (Square & V) ; different	Carry out visual inspection to ensure quality of welded	
metals- Aluminium,	joint.	
Stainless Steel; different	Inspect the weld using Dye-penetration Test	
position- 1F & 1G]	(DPT)/Magnetic particle Test (MPT).	
(NOS: CSC/N0212)	,, 18 11 11 11 11 11 11	
11. Perform Aluminium & MS	Plan and prepare development or edge preparation for	
pipe joint by GTAW in flat	specific type of pipe joint.	
position.	Mark and cut the MS pipe as per development.	
(NOS: CSC/N0212)	Select the type of welding current, size and type of	
(11001 000) 1101111	tungsten electrode, size of nozzle, gas flow rate and	
	welding current as per requirement.	
	Set and tack the piece as per drawing.	
	Deposit the weld bead maintaining proper technique and	
	safety aspects.	
	Inspect the welded joint visually for root penetration,	
	bead uniformity and surface defects.	
12. Set the Plasma Arc cutting	Plan and mark on Ferrous/Non ferrous metal plates	
machine and cut ferrous	surface for plasma cutting.	
&non-ferrous metals.	Select the torch/nozzle size, current and working pressure	
(NOS: CSC/N0207)	of gas as per requirement.	
,	Set the marked plate properly on cutting table.	
	Set the plasma cutting machine and perform the cutting	
	operation by adapting proper techniques and safety	



	acnosts		
	aspects.		
	Clean and inspect the cut surface for quality of cutting.		
13. Set the resistance spot welding machine and join	Plan and select the material and clean the surface thoroughly.		
MS & SS sheet.	Set the spot welding parameters on machine.		
(NOS: CSC/N0206)	Spot weld the joint adapting appropriate techniques and safety.		
	Inspect the joint for soundness of weld.		
14. Perform joining of different similar and dissimilar metals	Plan and select the nozzle size, working pressure type of flame, filler rod and flux as per requirement.		
by brazing operation as per	Prepare, set and tack the pieces as per drawing.		
standard procedure. [different similar and	Braze the joint adapting proper brazing technique and safety aspect.		
dissimilar metals- Copper, MS, SS] CSC/N9410	Carry out visual inspection to ascertain quality weld joint.		
15. Repair Cast Iron machine	Plan and prepare the job as per requirement.		
parts by selecting	Select the type & size of electrode, power source, polarity,		
appropriate welding	welding current as per requirement.		
process. [Appropriate	Set the part properly.		
welding process- OAW,	Deposit the weld adapting appropriate welding technique		
SMAW] <i>CSC/N9411</i>	and safety aspects.		
	Clean the welded joint thoroughly.		
	Carry out visual inspection to ascertain quality of weld joint.		
	17		
16. Hard facing of alloy steel components / MS rod by	Plan and prepare the component by cleaning the surface thoroughly.		
using hard facing electrode. CSC/N9412	Select the type & size of electrode, power source, welding current as per requirement.		
	Deposit the weld observing standard practice and safety.		
	Clean the welded surface thoroughly.		
	Carryout visual inspection to ascertain quality of weld.		
	,,		
17. Read and apply engineering	Read & interpret the information on drawings and apply in		
drawing for different	executing practical work.		
application in the field of	Read &analyze the specification to ascertain the material		
work. CSC/N9401	requirement, tools and assembly/maintenance parameters.		
	Encounter drawings with missing/unspecified key		
	information and make own calculations to fill in missing		



	dimension/parameters to carry out the work.
18. Demonstrate basic	Solve different mathematical problems
mathematical concept and principles to perform practical operations. Understand and explain basic science in the field of study. CSC/N9402	Explain concept of basic science related to the field of study



## **SYLLABUS - WELDER**

#### **DURATION: ONE YEAR**

DURATION: ONE YEAR			
Duration	Reference Learning Outcome	Process code	Professional Skills (Trade Practical) With Indicative Hrs.  Professional Knowledge (Trade Theory)
Professional Skill 47Hrs; Professional Knowledge 11Hrs	Set the gas welding plant and join MS sheet in different position following safety precautions. [Different position: -1F, 2F, 3F, 1G, 2G, 3G.]  Set the SMAW machine and perform different type of joints on MS in different position observing standard procedure. [different types of joints- Fillet (T-joint, lap & Corner), Butt (Square & V); different position - 1F, 2F, 3F,4F, 1G, 2G, 3G, 4G] (Mapped NOS: CSC/NO2O4)	OAW-01	<ul> <li>1. Demonstration of Machinery used in the trade.</li> <li>2. Identification to safety equipment and their use etc.</li> <li>3. Hack sawing, filing square to dimensions.</li> <li>4. Marking out on MS plate and punching.</li> <li>5. Setting of oxy-acetylene welding equipment, Lighting and setting of flame.</li> <li>6. Perform fusion run without filler rod on MS sheet 2mm thick in flat position.</li> <li>7. Setting up of Arc welding machine &amp; accessories and striking an arc.</li> <li>8. Deposit straight line bead on MS plate in flat position.</li> <li>1. Importance of trade Training.  - General discipline in the Institute - Elementary First Aid Importance of Welding in Industry - Safety precautions in Shielded Metal Arc Welding, and Oxy-Acetylene Welding, and Oxy-Acetylene Welding and Cutting.</li> <li>- Arc and Gas Welding Equipments, tools and accessories Various Welding Processes and its applications Arc and Gas Welding terms and definitions.</li> </ul>
Professional Skill 21Hrs; Professional Knowledge 05Hrs	Set the gas welding plant and join MS sheet in different position following safety precautions.	OAW-02	9. Depositing bead with filler rod on M.S. sheet 2 mm thick in flat position.  - Different process of metal joining methods: Bolting, riveting, soldering, brazing, seaming etc.  - Types of welding joints and
	[Different position: - 1F, 2F, 3F, 1G, 2G,	OAW-03	10. Edge joint on MS sheet its applications. Edge 2 mm thick in flat preparation and fit up for



	3G.]		position without filler rod.	different thickness Surface Cleaning
Professional Skill 20Hrs; Professional Knowledge	Set the SMAW machine and perform different type of joints on MS in different	SMAW-02	11. Straight line beads on M.S. plate 10 mm thick in flat position.	
05Hrs	position observing standard procedure. [different types of joints- Fillet (T-joint, lap & Corner), Butt (Square & V); different position - 1F, 2F, 3F,4F, 1G, 2G, 3G, 4G] (Mapped NOS: CSC/N0204)	SMAW-03	12. Weaved bead on M. S plate 10mm thick in flat position.	<ul> <li>Heat and temperature and its terms related to welding</li> <li>Principle of arc welding. And characteristics of arc.</li> </ul>
Professional Skill 23Hrs; Professional	Set the oxy- acetylene cutting plant and perform different	OAGC-01	13. Setting up of oxy- acetylene and make straight cuts (freehand)	<ul> <li>Common gases used for welding &amp; cutting, flame temperatures and uses.</li> </ul>
Knowledge 05Hrs	cutting operations on MS plate. [Different cutting operation – Straight, Bevel, circular] ( Mapped NOS:	OAGC-02	14. Perform marking and straight line cutting of MS plate 10 mm thick by gas. Accuracy within ±2mm.  15. Beveling of MS plates	flames and uses.
	CSC/N0201)	OAGC-03	10 mm thick, cutting regular geometrical shapes and irregular shapes, cutting chamfers by gas cutting.  16. Marking and perform radial cuts, cutting out	
		OAGC-04	holes using oxy- acetylene gas cutting. 17. Identify cutting defects viz., distortion, grooved,	
		OAGC-05	fluted or ragged cuts; poor draglines; rounded edges; tightly adhering slag.	
		OAGC-06		



Professional Skill 126Hrs; Professional Knowledge 31Hrs	Set the gas welding plant and join MS sheet in different position following safety precautions. [Different position: - 1F, 2F, 3F, 1G, 2G, 3G.]  Set the SMAW	OAW-04 SMAW-04 OAW-05	<ul> <li>18. Square butt joint on M.S. sheet 2 mm thick in flat Position. (1G)</li> <li>19. Fillet "T" joint on M.S. Plate 10 mm thick in flat position. (1F)</li> <li>20. Open corner joint on MS sheet 2 mm thick in flat Position (1F)</li> </ul>	sources: Transformer, Rectifier and Inverter type welding machines and its care &maintenance Advantages and disadvantages of A.C. and D.C. welding machines
	machine and perform different type of joints on MS in different position observing standard procedure. [different types of joints- Fillet ( T-joint, lap & Corner), Butt	OAW-06	<ul> <li>21. Fillet lap joint on M.S. plate 10 mm thick in flat position. (1F)</li> <li>22. Fillet "T" joint on MS sheet 2 mm thick in flat position. (1F)</li> <li>23. Open Corner joint on MS plate 10 mm thick in flat position. (1F)</li> </ul>	<ul> <li>Welding positions as per EN &amp;ASME: flat, horizontal, vertical and over head position.</li> <li>Weld slope and rotation.</li> <li>Welding symbols as per BIS &amp; AWS.</li> </ul>
	(Square & V); different position - 1F, 2F, 3F,4F, 1G, 2G, 3G, 4G] ( Mapped NOS: CSC/N0204)	OAW-07 SMAW-07	<ul> <li>24. Fillet Lap joint on MS sheet 2 mm thick in flat position. (1F)</li> <li>25. Single "V" Butt joint on MS plate 12 mm thick in flat position (1G).</li> </ul>	_ · · ·
		I&T-01	<ul><li>26. Testing of weld joints by visual inspection.</li><li>27. Inspection of welds by using weld gauges.</li></ul>	and defective welds
		OAW-08	28. Square Butt joint on M.S. sheet. 2 mm thick in Horizontal position. (2G) 29. Straight line beads and multi layer practice on M.S. Plate 10 mm thick	<ul> <li>Calcium carbide uses and hazard.</li> <li>Acetylene gas properties and flash back arrestor.</li> </ul>
		SMAW-09 OAW-09	in Horizontal position. 30. Fillet "T" joint on M.S. plate 10 mm thick in Horizontal position. (2F) 31. Fillet Lap joint on M.S.	- Oxygen gas and its
			sheet 2 mm thick in horizontal position <b>(2F)</b> 32. Fillet Lap joint on M.S.	properties, uses in welding Charging process of oxygen



			plate 10 mm thick in	and acetylene gases
		SMAW-10	horizontal position. (2F)	- Oxygen and Dissolved
				Acetylene gas cylinders
				and Color coding for
				different gas cylinders.
				- Uses of single and double
				stage Gas regulators.
		OAW-10	33. Fusion run with filler	- Oxy acetylene gas welding
			rod in vertical position	Systems (Low pressure and
			on 2mm thick M.S	High pressure).
			sheet.	Difference between gas
		OAW-11		welding blow pipe(LP &HP)
			M.S. sheet. 2 mm thick	and gas cutting blow pipe
			in vertical position (3G)	- Gas welding techniques.
		6. 4 4 4	35. Single Vee Butt joint on	Rightward and Leftward
		SMAW-11	M.S. plate 12 mm thick	techniques.
			in horizontal position	
		CD 4 A VA 4 A 2	(2G).	0 1-1-
		SMAW- 12	36. Fillet "T" joint on M.S	- Arc blow – causes and
			sheet 2 mm thick in	methods of controlling.
		OAW-12	vertical position. <b>(3F)</b> 37. Fillet "T" joint on M.S.	- Distortion in arc & gas welding and methods
		UAW-12	plate 10 mm thick in	employed to minimize
			vertical position. (3F)	distortion
			vertical position. (31)	- Arc Welding defects,
		SMAW-13		causes and Remedies.
Professional	Set the SMAW	OAW-13	38. Structural pipe welding	- Specification of pipes,
Skill 80 Hrs;	machine and perform		butt joint on MS pipe Ø	various types of pipe
Professional	different type of joints		50 and 3mm WT in 1G	joints, pipe welding all
Knowledge	on MS in different		position.	positions, and procedure.
17Hrs	position observing	SMAW-14	39. Fillet Lap joint on M.S.	- Difference between pipe
	standard procedure.		Plate 10 mm in vertical	welding and plate welding.
	[different types of		position. <b>(3G)</b>	
	joints- Fillet ( T-joint,	SMAW-15	40. Open Corner joint on	, · · · · · · · · · · · · · · · · · · ·
	lap & Corner), Butt		MS plate 10 mm thick in	Elbow joint, "T" joint, Y
	(Square & V); different		vertical position. (2F)	joint and branch joint
	position - 1F, 2F,		41. Pipe welding - Elbow	
	3F,4F, 1G, 2G, 3G, 4G]	OAW-14	joint on MS pipe Ø 50	system
	(Mapped NOS:		and 3mm WT. <b>(1G)</b>	
	CSC/N0204)	OAW-15	, ,	- Gas welding filler rods,
	Perform welding in		on MS pipe Ø 50 and	specifications and sizes.
	different types of MS		3mm WT. <b>(1G)</b>	- Gas welding fluxes – types
	pipe joints by Gas			and functions.



	welding (OAW). [Different types of MS	SMAW-16	MS plate12 mm thick in	principles, types fluxes &
	pipe joints — Butt, Elbow, T-joint, angle (45°) joint, flange		vertical position (3G).	uses - Gas welding defects, causes and remedies
	joint] (NOS: CSC/N0204)	OAW-16	joint on MS pipe Ø 50 and 3mm WT. <b>(1G)</b>	of flux, coating factor, sizespecifications of electrode.
		SMAW-17	45. Straight line beads on M.S. plate 10mm thick in over head position.	<ul><li>Effects of moisture pick up.</li><li>Storage and baking of electrodes.</li></ul>
Professional Skill 61Hrs; Professional Knowledge 06Hrs	Set the SMAW machine and perform different type of joints on MS in different position observing	SMAW-18	46. Pipe Flange joint on M.S plate with MS pipe Ø 50 mm X 3mm WT (1F)	1
	standard procedure. [different types of joints- Fillet ( T-joint,	SMAW-19	47. Fillet "T" joint on M.S. plate 10 mm thick in over head position. (4F)	·
	lap & Corner), Butt (Square & V); different position - 1F, 2F, 3F,4F, 1G, 2G, 3G, 4G] (Mapped NOS:	SMAW-20 SMAW-21	on MS pipe Ø 50 and 5 mm WT. in 1G position. 49. Fillet Lap joint on M.S. plate 10 mm thick in	- Welding of low, medium and high carbon steel and alloy steels.
	Set the SMAW		over head position. (4G).	
	machine and perform welding in different types of MS pipe joints by SMAW.	SMAW-22	50. Single "V" Butt joint on MS plate 10mm thick inover head position (4G)	1
	[Different types of MS pipe joints — Butt, Elbow, T-joint, angle (45°) joint, flange joint] (NOS: CSC/N0204)	SMAW-23	51. Pipe butt joint on M. S. pipe Ø 50mm WT 6mm (1G Rolled).	
Professional Skill 25 Hrs; Professional Knowledge	Choose appropriate welding process and perform joining of different types of	OAW-17	52. Butt joint of copper pipe ½ inch by brazing process by induction welding machine	<ul> <li>Induction welding, brazing of copper tubes.</li> <li>Brass – types – properties and welding methods.</li> </ul>
04Hrs	metals and check its correctness. [appropriate welding	SMAW -24	53. Square Butt joint on S.S. Sheet 2 mm thick in flat position. (1G)	- Copper – types – properties and welding methods.



	process – OAW, SMAW; Different metal – SS, CI, Brass, Aluminium]	OAW-18	54. Corner/T joint of copper pipe of ½ inch and of length 75 mm	- Brazing cutting tools.
	(Mapped NOS: CSC/N0204)			
Professional Skill 21Hrs; Professional Knowledge 04Hrs	Choose appropriate welding process and perform joining of different types of metals and check its correctness.  [appropriate welding process – OAW, SMAW; Different metal – SS, CI, Brass, Aluminium]  (Mapped NOS: CSC/N0204)  Demonstrate arc gauging operation to rectify the weld joints.	OAW-19 SMAW-25 AG-01	<ul> <li>55. Square Butt &amp; Lap joint on M.S. sheet 2 mm thick by brazing in flat position.</li> <li>56. Single "V" butt joint C.I. plate 6mm thick in flat position. (1G)</li> <li>57. Arc gouging on MS plate 10 mm thick.</li> </ul>	<ul> <li>Aluminium properties and weldability, Welding methods</li> <li>Arc cutting &amp; gouging,</li> </ul>
Professional Skill 20Hrs; Professional Knowledge 04Hrs	Choose appropriate welding process and perform joining of different types of metals and check its correctness.  [appropriate welding process — OAW, SMAW; Different metal — SS, CI, Brass, Aluminium]  (Mapped NOS: CSC/NO204)	OAW-20	58. Square Butt joint on Aluminium sheet. 3 mm thick in flat position.(10hrs) 59. Bronze welding of cast iron (Single "V" butt joint) 6mm thick plate (10hrs)	types. 60. Welding methods of cast iron(04hrs)
Professional Skill 25 Hrs; Professional Knowledge 04Hrs	Test welded joints by different methods of testing. [different methods of testing-Dye penetration test, Magnetic particle test, Nick break test, Free band test, Fillet fracture test]	I&T-02 I&T-03 I&T-04 I&T-05 I&T-06	<ul><li>61. Dye penetrant test.</li><li>62. Magnetic particle test.</li><li>63. Nick- break test.</li><li>64. Free bend test.</li><li>65. Fillet fracture test.</li></ul>	<ul> <li>Types of Inspection methods</li> <li>Classification of destructive and NDT methods</li> <li>Welding economics and Cost estimation.</li> </ul>



	( Mapped NOS: CSC/N0204)				
Professional Skill 166Hrs; Professional Knowledge 32Hrs	Set GMAW machine and perform welding in different types of joints on MS sheet/plate by GMAW	GMAW- 01	66. 67.	Introduction to safety equipment and their use etc. Setting up of GMAW welding machine &	<ul> <li>Safety precautions in Gas         Metal Arc Welding and Gas         Tungsten Arc welding.</li> <li>Introduction to GMAW -         equipment – accessories.</li> </ul>
	in various positions by dip mode of metal transfer. [different types of joints- Fillet (T-joint, lap, Corner),	GMAW - 02	68.	accessories and striking an arc.  Depositing straight line beads on M.S Plate.	<ul> <li>Various other names of the process. (MIG/MAG/CO<sub>2</sub> welding.)</li> </ul>
	Butt (Square & V); various positions- 1F, 2F, 3F,4F, 1G, 2G, 3G] ( Mapped NOS:			Fillet weld – "T" joint on M.S plate 10mm thick in flat position by Dip transfer. (1F)	
	CSC/N0209)	GMAW -03	70.	Fillet weld – Lap joint on M.S. sheet 3mm thick in flat position by Dip transfer. (1F) Fillet weld – "T" joint	<ul> <li>Advantages of GMAW welding over SMAW , limitations and applications</li> <li>Process variables of</li> </ul>
		GMAW -04	72.	on M.S. sheet 3mm thick in flat position by Dip transfer. <b>(1F)</b> Fillet weld – corner	GMAW.
		GMAW -05		joint on M.S. sheet 3mm thick in flat position by Dip transfer. (1F)	
		GMAW -06	73. 74.	Butt weld – Square butt joint on M.S sheet 3mm thick in flat position (1G) Butt weld – Single "V"	<ul> <li>Wire feed system – types – care and maintenance.</li> <li>Welding wires used in GMAW, standard diameter and codification</li> </ul>
		GMAW -07		butt joint on M.S plate 10 mm thick by Dip transfer in flat position. (1G)	as per AWS.
		GMAW -08	75.	Fillet weld – "T" joint on M.S plate 10mm thick in Horizontal position by Dip	<ul> <li>Name of shielding gases used in GMAW and its applications.</li> <li>Flux cored arc welding – description</li> </ul>
			76.	transfer. <b>(2F)</b> Fillet weld – corner	description, advantage, welding wires, coding as



GMAW -09		joint on M.S plate 10mm thick in	per AWS.
		Horizontal position by Dip transfer. <b>(2F)</b>	
GMAW -10	77.	Fillet weld – "T" joint on M.S. sheet 3mm thick in Horizontal position by	<ul> <li>Edge preparation of various thicknesses of metals for GMAW.</li> <li>GMAW defects, causes and</li> </ul>
	78.	Dip transfer. <b>(2F)</b> Fillet weld – corner	remedies
GMAW -11		joint on M.S. sheet 3mm thick in Horizontal position by Dip transfer. (2F)	
GMAW -12	79.	Fillet weld – "T" joint on M.S plate 10mm thick in vertical position by Dip transfer. (3F)	<ul> <li>Heat input and techniques         of controlling heat input         during welding.</li> <li>Heat distribution and         effect of faster cooling</li> </ul>
GMAW -13	80.	Fillet weld – corner joint on M.S plate 10mm thick in vertical position by dip transfer. (3F)	
GMAW -14	81.	Fillet weld – Lap joint on M.S. sheet 3mm thick in vertical position by Dip transfer. (3F)	<ul><li>Pre heating &amp; Post Weld Heat Treatment</li><li>Use of temperature indicating crayons.</li></ul>
GMAW -15	82.	Fillet weld – corner joint on M.S. sheet 3mm thick in vertical position by Dip transfer. (3F)	
GMAW -16	83.	Fillet weld – Lap and "T" joint on M.S sheet 3mm thick inoverhead position by Dip transfer. (4F)	<ul> <li>Submerged arc welding process —principles, equipment, advantages and limitations</li> </ul>
GMAW -17	84.	Tee Joints on MS Pipe Ø 60 mm OD x 3 mm WT 1G position – Arc constant (Rolling)	



		GMAW -18	85.	Depositing bead on S.S sheet in flat	J
		GMAW -19	86.	position. Butt joint on Stainless steel 2 mm thick sheet in flat position by Dip transfer.	types, principles, equipments, Thermit mixture types and applications.  - Use of backing strips and backing bars
Professional Skill 80 Hrs; Professional Knowledge	Set the GTAW machine and perform welding by GTAW in different types of	GTAW -01	87.	Depositing bead on Aluminium sheet 2 mm thick in flat position.	- GTAW process - brief description. Difference between AC and DC welding, equipments,
14Hrs	joints on different metals in different position and check correctness of the	GTAW -02	88.	Square butt joint on Aluminium sheet 1.6mm thick in flat position.	polarities and applications Power sources for GTAW - AC &DC
	weld. [different types of joints- Fillet ( T- joint, lap, Corner), Butt (Square & V);	GTAW -03	89.	Fillet weld – "T" joint on Aluminium sheet 1.6 mm thick in flat position. (1F)	<ul> <li>Tungsten electrodes –</li> <li>types &amp; uses, sizes and</li> <li>preparation</li> <li>GTAW Torches- types,</li> </ul>
	different metals- Aluminium, Stainless Steel; different position- 1F & 1G] ( Mapped NOS:	GTAW -04	90.	Fillet weld – Outside corner joint on Aluminium sheet 2 mm thick in flat position. (1F)	parts and their functions
	CSC/N0212)	GTAW -05	91.	Butt weld - Square butt joint on Stainless steel sheet 1.6 mm thick in flat position with purging gas (1G)	<ul> <li>Edge preparation and fit up.</li> <li>GTAW parameters for welding of different thickness of metals</li> </ul>
		GTAW -06	92.	Fillet weld – "T" joint on Stainless steel sheet 1.6 mm thick in flat position. (1F)	<ul><li>Argon / Helium gas properties – uses.</li><li>GTAW Defects, causes and remedy.</li></ul>
Professional Skill 20Hrs; Professional Knowledge 04Hrs	Perform Aluminium & MS pipe joint by GTAW in flat position. ( Mapped NOS: CSC/N0212)	GTAW -07	93.	Pipe butt joint on Aluminium pipe Ø 50 mm x 3 mm WT in Flat position. (1G)	<ul><li>Friction welding process- equipment and application</li><li>Laser beam welding (LBW).</li></ul>
Professional Skill 20Hrs; Professional Knowledge	Perform Aluminium & MS pipe joint by GTAW in flat position. ( Mapped NOS:	GTAW -08	94.	"T" Joints on MS Pipe Ø 50 mm OD x 3 mm WT, position – Flat (1F)	<ul> <li>Plasma Arc Welding (PAW)</li> <li>and cutting (PAC) process</li> <li>equipments and principles of operation.</li> </ul>
03Hrs	CSC/N0212)	PAC-01	95.	Straight cutting on	- Types of Plasma arc,



	Set the Plasma Arc cutting machine and cut ferrous & nonferrous metals.  ( Mapped NOS: CSC/NO207)		ferrous and non advantages applications.	and
Professional Skill 20Hrs; Professional Knowledge 02Hrs	Set the resistance spot welding machine and join MS & SS sheet. ( Mapped NOS: CSC/N0206)	RW-01	<ul> <li>6. Lap joint on Stainless steel sheet by Resistance Spot welding.</li> <li>7. MS sheets joining by Resistance Spot welding</li> <li>8. Applications limitations</li> <li>9. Applications limitations</li> <li>10. Applications limitations</li> <li>10. Applications limitations</li> </ul>	
Professional Skill 41Hrs; Professional Knowledge 10Hrs	Perform joining of different similar and dissimilar metals by brazing operation as per standard procedure. [different similar and dissimilar metals- Copper, MS, SS] CSC/N9410	OAW-01	8. Square butt joint on Copper sheet 2mm thick in flat position. (1G) 9. "T" joint on Copper to MS sheet 2mm thick in flat position by Brazing (1F)  - Metalizing — ty metalizing principl principle principles of operations	es. acetylene process-
		OAW-04	Sheet with copper drawing sheet "T" joint Welding P  O1. Silver brazing on Specification (WI	rocedure PS) and
Professional Skill 24Hrs; Professional Knowledge 01Hrs	Repair Cast Iron machine parts by selecting appropriate welding process. [Appropriate welding process- OAW, SMAW] CSC/N9411  Hard facing of alloy steel components / MS rod by using hard	OAW - 05  SMAW-01	broken C.I. machine parts by oxy-acetylene welding with C.I and bronze filler rod.  03. Repair welding of broken C.I machine parts by C.I. electrode.  04. Repair plastic broken parts or pipes by plastic welding welding Polyvinylchloride (PE)	and d facing. machine nd plastic
	facing electrode. CSC/N9412		machine. 05. Make a plastic tank with plastic sheet of PVC. Dimensions 150*100*100	



Engineering Drawing: 40 Hrs.					
Professional	Read and apply	ENGINEERING DRAWING :			
Knowledge	engineering drawing	- Introduction to Engineering Drawing and Drawing Instruments;			
	for different	Conventions			
ED - 40 hrs.	application in the field	Sizes and layout of drawing sheets			
	of work. CSC/N9401	Title Block, its position and content			
		Drawing Instrument			
		- Free hand drawing of; Geometrical figures and blocks with dimension			
		Transferring measurement from the given object to the free hand			
		sketches.			
		Free hand drawing of hand tools and measuring tools.			
		- Lines			
		Types and applications in drawing			
		- Drawing of Geometrical figures;			
		Angle, Triangle, Circle, Rectangle, Square, Parallelogram.			
		Lettering & Numbering – Single Stroke, double stroke, inclined			
		- Reading of dimension and Dimensioning Practice.			
		-Reading of fabrication drawing, sectional view of different types of			
		welding Joints. Sectional view of different pipe joints			
		- Symbolic representation			
		different symbols used in the related trades			
		Reading of Job Drawing of related trades.			
		rkshop Calculation & Science: 38 Hrs.			
Professional	Demonstrate basic	WORKSHOP CALCULATION & SCIENCE :			
Knowledge	mathematical concept	- Unit, Fractions			
	and principles to	- Square root, Ratio and Proportions, Percentage			
WC- 38 hrs.	perform practical	- Material Science			
	operations.	- Mass, Weight, Volume and Density			
	Understand and	- Heat & Temperature and Pressure			
	explain basic science	- Basic Electricity			
	in the field of study.	- Mensuration			
	CSC/N9402	- Trigonometry			



## **SYLLABUS FOR CORE SKILLS**

1. Employability Skills (Common for all CTS trades) (120 hrs)

Learning outcomes, assessment criteria, syllabus and Tool List of Core Skills subjects which is common for a group of trades, provided separately in <a href="www.bharatskills.gov.in">www.bharatskills.gov.in</a> / dgt.gov.in



## **ANNEXURE-I**

	LIST OF TOOLS AND EQUIPMENT				
	WELDER (For batc	h of 20 Candidates)			
S No.	Name of the Tools& Equipment	Specification	Quantity		
A. TRA	NINEES TOOL KIT ( For each additional unonally)	nit trainees tool kit SI. 1-15 is	required		
1.	Welding helmet fiber		20+1 Nos.		
2.	Welding hand shield fiber		20+1 Nos.		
3.	Chipping hammer	with metal handle 250 Grams	20+1 Nos.		
4.	Chisel cold	flat 19 mm x 150 mm	20+1 Nos.		
5.	Centre punch	9 mm x 127 mm	20+1 Nos.		
6.	Dividers	200 mm	20+1 Nos.		
7.	Stainless steel rule	300mm	20+1 Nos.		
8.	Scriber	150 mm double point	20+1 Nos.		
9.	Flat Tongs	350mm long	20+1 Nos.		
10.	Hack saw frame	fixed 300 mm	20+1 Nos.		
11.	File half round	bastard 300 mm	20+1 Nos.		
12.	File flat	350 mm bastard	20+1 Nos.		
13.	Hammer ball pane	1 kg with handle	20+1 Nos.		
14.	Tip Cleaner		20+1 Nos.		
15.	Try square	6"	20+1 Nos.		
B. INSTRUMENTS AND GENERAL SHOP OUTFIT - For 2 (1+1) units no additional items are required  TOOLS & EQUIPMENT					
10013	·		9 Nos /2 for		
16.	Spindle key		8 Nos. (2 for each type of gas)		
17.	Screw Driver	300mm blade and 250 mm blade	1 each		
18.	Number punch	6 mm	2 set		
19.	Letter punch	6 mm	2 set		



20.	Magnifying glass	100 mm dia.	2 Nos.
21.	Universal Weld measuring gauge		2 Nos.
22.	Spanner D.E.	6 mm to 32mm	2 sets
23.	C-Clamps	10 cm and 15 cm	2 each
24.	Hammer sledge	double faced 4 kg	2 No.
25.	S.S tape	5 meters flexible in case	5 No.
26.	H.P. Welding torch	with 5 nozzles	2 sets
27.	Oxygen Gas Pressure	regulator double stage	2 Nos.
28.	Acetylene Gas Pressure	regulator double stage	2 Nos.
29.	CO <sub>2</sub> Gas pressure regulator	with flow meter	2 set
30.	Argon Gas pressure regulator	with flow meter	2 set
31.	Metal rack	182 cm x 152 cm x 45 cm	1 No.
32.	First Aid box		1 No.
33.	Steel lockers	with 8 Pigeon holes	2 Nos.
34.	Steel almirah / cupboard		4 Nos.
35.	Black board and easel with stand		1 No.
36.	Flash back arrester (torch mounted)		4 pairs
37.	Flash back arrester (cylinder		4 pairs
57.	mounted)		4 pan 3
38.	Multiangle magnetic clamp set	Metal base (18x10x10 cm)	one
GENER	RAL SHOP OUTFIT		
		with all accessories	1 set
39.	Welding Transformer	(400A, OCV 60-100 V,	
		60% duty cycle)	
	Welding Transformer (or) Inverter	with all accessories	1 set
40.	based welding machine (IGBT)	(300A, OCV 60 – 100 V,	
	based welding machine (IGBT)	60% duty cycle)	
41.	D.C Arc welding rectifiers set with all	(400 A. OCV 60 – 100 V,	1 sets
	accessories	60% duty cycle )	
		400A capacity with air	1 set
42.	GMAW welding machine	cooled torch, Regulator,	
	ennite meianig maeinie	Gas pre-heater, Gas hose	
		and Standard accessories	
		with water cooled torch	1 set
	100/2007	300 A, Argon regulator,	
43.	AC/DC GTAW welding machine	Gas hose, water	
		circulating system and	
		standard accessories.	_
		with all accessories,	1 set
44.	Air Plasma cutting equipment	capacity to cut 12 mm	
		clear cut	4.1
45.	Air compressor suitable for above air	Two stage compressor	1 No.



46. Auto Darkening Welding Helmet  47. Spot welding machine  48. Portable gas cutting machine (PUG)  48. Pedestal grinder fitted with coarse and medium grain size grinding wheels  49. Bench grinder fitted with fine grain size silicon carbide green grinding wheel  50. Suitable gas welding table with positioner 6 Nos.  51. AG 4 Grinder  52. Suitable gas welding table with positioner 6 Nos.  53. Suitable Arc welding table with positioner 6 Nos.  54. Trolley for cylinder (H.P. Unit) 2 Nos.  55. Hand shearing machine capacity flats  57. Power saw machine (Cap. 6 mm) 1 No.  58. Power saw machine (Cap. 6 mm) 1 No.  59. Work bench 2 340x120x75 cm with 4 bench vices of 150 mm jaw opening  60. Oxy Acetylene Gas cutting blow pipe 1 Oxygen, Acetylene Cylinders* 2 Nos.  4 Argon gas cylinder ** 2 Nos.  61. Argon gas cylinder ** 2 Nos.  62. CO2 cylinder ** 2 Nos.  63. Argon gas cylinder ** 2 Nos.  64. Arivil 24 sq. inches working area with stand 5. Swage block 5048 Cast iron 16x16x16 inch 1 No.  65. Swage block 5048 Cast iron 16x16x16 inch 1 No.  66. Magnetic particle testing Kit # 1 1 No.  67. Fire extinguishers (foam type and CO2type) 6. Sittable Gas cutting table 1 No.  59. Volutable Gas cutting table 1 No.		plasma cutting system.	15KW	
48. Portable gas cutting machine (PUG)  Pedestal grinder fitted with coarse and medium grain size grinding wheels  Bench grinder fitted with fine grain size silicon carbide green grinding wheel  15. AG 4 Grinder  Suitable gas welding table with fire bricks 2 Nos.  Suitable Arc welding table with positioner 6 Nos.  Suitable Arc welding table with positioner 6 Nos.  Trolley for cylinder (H.P. Unit) 2 Nos.  Sol. Power saw machine capacity flats  Portable drilling machine (Cap. 6 mm) 1 No.  Oven, electrode drying 0 to 350°C, 10 kg capacity, 4 depth 450mm to 500 mm, intake capacity, 10 kg 340x120x75 cm with 4 bench vices of 150 mm jaw opening  Work bench 2 Nos.  340x120x75 cm with 4 bench vices of 150 mm jaw opening  60. Oxy Acetylene Gas cutting blow pipe 61. Oxygen, Acetylene Cylinders ** 2 Nos.  Argon gas cylinder ** 2 each 62. CO2 cylinder ** 2 Nos.  Anvil 24 sq. inches working area with stand  65. Swage block 5048 Cast iron 16x16x16 inch 1 No.  66. Magnetic particle testing Kit # 1 set  Fire extinguishers (foam type and CO2type)  68. Fire buckets with stand 4 Nos.  69. Portable draise machine capacity in the scape of the control of the control of the capacity of t	46.	Auto Darkening Welding Helmet		5Nos.
48. Portable gas cutting machine (PUG)  Pedestal grinder fitted with coarse and medium grain size grinding wheels  Bench grinder fitted with fine grain size silicon carbide green grinding wheel  50. Suitable gas welding table with fire bricks 2 Nos.  51. AG 4 Grinder  52. Suitable gas welding table with positioner 6 Nos.  53. Suitable Arc welding table with positioner 6 Nos.  54. Trolley for cylinder (H.P. Unit) 2 Nos.  55. Hand shearing machine capacity flats  66. Power saw machine 18" or blade size 450 mm 1 No.  77. Portable drilling machine (Cap. 6 mm) 1 No.  78. Oven, electrode drying 0 to 350°C, 10 kg capacity, depth 450mm to 500 mm, intake capacity 10 kg 340x120x75 cm with 4 bench vices of 150 mm jaw opening 9 Oxygen, Acetylene Cylinders** 2 Ros.  60. Oxy Acetylene Gas cutting blow pipe 61. Oxygen, Acetylene Cylinders** 2 Ros.  63. Argon gas cylinder ** 2 Ros.  64. Arvil 24 sq. inches working area with stand 65. Swage block 5048 Cast iron 16x16x16 inch 1 No.  66. Magnetic particle testing Kit # 1 set Fire extinguishers (foam type and CO2type) Portable darasive cut-off machine 1 No.	47.	Spot welding machine	15 KVA with all	1 set
48. Portable gas cutting machine (PUG)  Pedestal grinder fitted with coarse and medium grain size grinding wheels  Bench grinder fitted with fine grain size silicon carbide green grinding wheel  51. AG 4 Grinder  52. Suitable gas welding table with fire bricks 2 Nos.  53. Suitable Arc welding table with positioner 6 Nos.  54. Trolley for cylinder (H.P. Unit) 2 Nos.  55. Hand shearing machine capacity flats  56. Power saw machine 18" or blade size 450 mm  57. Portable drilling machine (Cap. 6 mm) 1 No.  58. Oven, electrode drying 0 to 350°C, 10 kg capacity, depth 450mm to 500 mm, intake capacity 10 kg  59. Work bench 2 Sets  60. Oxy Acetylene Gas cutting blow pipe 61. Oxygen, Acetylene Cylinders ** 2 Nos.  61. Agon gas cylinder ** 2 Nos.  62. CO2 cylinder ** 2 Nos.  63. Argon gas cylinder ** 2 Nos.  64. Anvil 24 sq. inches working area with stand 65. Swage block 5048 Cast iron 16x16x16 inch 1 No.  66. Magnetic particle testing Kit # 1 set Fire extinguishers (foam type and CO2type) 66. Fire buckets with stand 4 Nos.  69. Portable abrasive cut-off machine 1500 mm dia.  2 Nos Michael Science Scien			accessories	
A9. Pedestal grinder fitted with coarse and medium grain size grinding wheels  Bench grinder fitted with fine grain size stilicon carbide green grinding wheel  51. AG 4 Grinder  52. Suitable gas welding table with fire bricks 2 Nos.  53. Suitable Arc welding table with positioner 6 Nos.  54. Trolley for cylinder (H.P. Unit) 2 Nos.  55. Hand shearing machine capacity flats  56. Power saw machine 18" or blade size 450 mm 1 No.  57. Portable drilling machine (Cap. 6 mm) 1 No.  Oven, electrode drying 0 to 350°C, 10 kg capacity, depth 450 mm to 500 mm, intake capacity 10 kg  59. Work bench 340x120x75 cm with 4 bench vices of 150 mm jaw opening 4 sets  60. Oxy Acetylene Gas cutting blow pipe 61. Oxygen, Acetylene Cylinders ** 2 Nos.  63. Argon gas cylinder ** 2 Nos.  64. Anvil 24 sq. inches working area with stand 65. Swage block 5048 Cast iron 16x16x16 inch 1 No.  67. Co2 type) 68. Fire buckets with stand 69. Portable abrasive cut-off machine 150 mm dia.  150 mm dia.  2 No.  150 mm dia.  2 Nos.  2 Nos.  1 No.  2 Nos.  2 Nos.  2 Nos.  340x120x75 cm with 4 bench vices of 150 mm jaw opening 2 sets  2 sets  2 sets  2 Nos.  340x120x75 cm with 4 bench vices of 150 mm jaw opening 4 sets  340x120x75 cm with 4 bench vices of 150 mm jaw opening 2 sets  340x120x75 cm with 4 bench vices of 150 mm jaw opening 2 sets  550. Oxygen, Acetylene Cylinders **  2 Nos.  561. Argon gas cylinder **  1 No.  572. Coz tiron 16x16x16 inch 1 No.  573. Fire extinguishers (foam type and CO2type)  574. Fire extinguishers (foam type and CO2type)  575. Fire buckets with stand 4 Nos.			capable of cutting Straight	1 set
Pedestal grinder fitted with coarse and medium grain size grinding wheels  Bench grinder fitted with fine grain size silicon carbide green grinding wheel  50. size silicon carbide green grinding wheel  51. AG 4 Grinder  52. Suitable gas welding table with positioner  53. Suitable Arc welding table with positioner  54. Trolley for cylinder (H.P. Unit)  55. Hand shearing machine capacity  60. Power saw machine  61. Oven, electrode drying  62. Oven, electrode drying  63. Work bench  64. Oxy Acetylene Gas cutting blow pipe  66. Oxy Acetylene Gas cutting blow pipe  67. Oxy Acetylene Cylinders**  68. Argon gas cylinder **  69. Anvil 24 sq. inches working area with stand  69. Portable abrasive cut-off machine  60. Magnetic particle testing Kit #  Fire extinguishers (foam type and CO2type)  68. Fire buckets with stand  69. Portable abrasive cut-off machine	48.	Portable gas cutting machine (PUG)		
49. and medium grain size grinding wheels  Bench grinder fitted with fine grain size silicon carbide green grinding wheel  51. AG 4 Grinder  52. Suitable gas welding table  53. Suitable Arc welding table  54. Trolley for cylinder (H.P. Unit)  55. Hand shearing machine capacity  56. Power saw machine  57. Portable drilling machine  58. Oven, electrode drying  58. Work bench  59. Work bench  60. Oxy Acetylene Gas cutting blow pipe  61. Oxygen, Acetylene Cylinders*  62. CO2 cylinder **  63. Argon gas cylinder **  64. Anvil 24 sq. inches working area with stand  65. Swage block 5048  66. Magnetic particle testing Kit #  67. CO2type)  68. Fire buckets with stand  69. Portable abrasive cut-off machine  150 mm dia.  1 No.  150 mm dia.  1 No.  1 No.  2 Nos.  2 Sets  1 No.  2 Sets  2 Sets  2 Nos.  2 Nos.  2 Nos.  2 Nos.  4 Sets iron 16x16x16 inch  1 No.  4 Nos.  4 Nos.  4 Nos.			accessories	
wheels  Bench grinder fitted with fine grain size silicon carbide green grinding wheel  51. AG 4 Grinder  52. Suitable gas welding table with positioner 6 Nos.  53. Suitable Arc welding table with positioner 6 Nos.  54. Trolley for cylinder (H.P. Unit) 2 Nos.  55. Hand shearing machine capacity flat of the power saw machine 18" or blade size 450 mm 1 No.  56. Power saw machine (Cap. 6 mm) 1 No.  57. Portable drilling machine (Cap. 6 mm) 1 No.  58. Voven, electrode drying 0 to 350°C, 10 kg capacity, depth 450mm to 500 mm, intake capacity 10 kg 340x120x75 cm with 4 bench vices of 150 mm jaw opening 2 sets  60. Oxy Acetylene Gas cutting blow pipe 2 sets  61. Oxygen, Acetylene Cylinders ** 2 Poss.  62. CO2 cylinder ** 2 Poss.  63. Argon gas cylinder ** 2 Poss.  64. Anvil 24 sq. inches working area with stand  65. Swage block 5048 Cast iron 16x16x16 inch 1 No.  66. Magnetic particle testing Kit # 1 set  67. CO2type)  68. Fire buckets with stand 4 Nos.  69. Portable abrasive cut-off machine 150 mm this particle testing Kit # 1 No.		Pedestal grinder fitted with coarse	300 mm dia.	2 No.
Bench grinder fitted with fine grain size silicon carbide green grinding wheel  51. AG 4 Grinder 52. Suitable gas welding table 53. Suitable Arc welding table 54. Trolley for cylinder (H.P. Unit) 55. Hand shearing machine capacity 56. Power saw machine 57. Portable drilling machine 58. Oven, electrode drying 59. Work bench 59. Argon gas cylinder ** 60. Oxy Acetylene Gas cutting blow pipe 61. Oxygen, Acetylene Cylinders ** 62. CO2 cylinder ** 63. Argon gas cylinder ** 64. Anvil 24 sq. inches working area with stand 66. Magnetic particle testing Kit # 67. CO2type) 68. Fire buckets with stand 69. Portable abrasive cut-off machine  150 mm dia. 150 nos. 150 nos. 150 mm dia. 150 nos. 150 mm dia. 150 nos. 150 nos. 150 d. 4 nos. 150 mm dia. 150 nos. 150 d. 4 nos. 150 mm dia. 150 nos. 150 d. 4 nos. 150 mm dia. 150 nos. 150 d. 4 nos. 150 mm dia. 150 nos. 150 d. 4 nos. 150 mm dia. 150 nos. 150 d. 4 nos. 150 mm dia. 150 nos. 150 d. 4 nos	49.	and medium grain size grinding		
Size silicon carbide green grinding wheel   150 mm dia.				
wheel  51. AG 4 Grinder  52. Suitable gas welding table  53. Suitable Arc welding table  54. Trolley for cylinder (H.P. Unit)  55. Hand shearing machine capacity  56. Power saw machine  57. Portable drilling machine  Coven, electrode drying  58. Work bench  59. Work bench  59. Work bench  60. Oxy Acetylene Gas cutting blow pipe  61. Oxygen, Acetylene Cylinders**  62. CO2 cylinder **  63. Argon gas cylinder **  64. Anvil 24 sq. inches working area with stand  66. Magnetic particle testing Kit #  67. Fire extinguishers (foam type and CO2type)  68. Fire buckets with stand  69. Portable abrasive cut-off machine				1 No.
51.AG 4 Grinder4 Nos.52.Suitable gas welding tablewith fire bricks2 Nos.53.Suitable Arc welding tablewith positioner6 Nos.54.Trolley for cylinder (H.P. Unit)2 Nos.55.Hand shearing machine capacitycut 6 mm sheets and flats1 No.56.Power saw machine18" or blade size 450 mm1 No.57.Portable drilling machine(Cap. 6 mm)1 No.0 Ven, electrode drying0 to 350°C, 10 kg capacity, depth 450mm to 500 mm,intake capacity 10 kg1 No.58.340x120x75 cm with 4 bench vices of 150 mm jaw opening4 sets60.Oxy Acetylene Gas cutting blow pipe2 sets61.Oxygen, Acetylene Cylinders **2 each62.CO2 cylinder **2 Nos.63.Argon gas cylinder **2 Nos.64.Anvil 24 sq. inches working area with stand1 No.65.Swage block 5048Cast iron 16x16x16 inch1 No.66.Magnetic particle testing Kit #1 set67.Fire extinguishers (foam type and CO2type)1. No.68.Fire buckets with stand4 Nos.69.Portable abrasive cut-off machine1 No.	50.		150 mm dia.	
52.Suitable gas welding tablewith fire bricks2 Nos.53.Suitable Arc welding tablewith positioner6 Nos.54.Trolley for cylinder (H.P. Unit)2 Nos.55.Hand shearing machine capacityCut 6 mm sheets and flats1 No.56.Power saw machine18" or blade size 450 mm1 No.57.Portable drilling machine(Cap. 6 mm)1 No.58.Oven, electrode drying0 to 350°C, 10 kg capacity, depth 450mm to 500 mm, intake capacity 10 kg1 No.59.Work bench340x120x75 cm with 4 bench vices of 150 mm jaw opening4 sets60.Oxy Acetylene Gas cutting blow pipe2 sets61.Oxygen, Acetylene Cylinders **2 each62.CO2 cylinder **2 Nos.63.Argon gas cylinder **2 Nos.64.Anvil 24 sq. inches working area with stand1 No.65.Swage block 5048Cast iron 16x16x16 inch1 No.66.Magnetic particle testing Kit #1 set67.Fire extinguishers (foam type and CO2type)1. No.68.Fire buckets with stand4 Nos.69.Portable abrasive cut-off machine1 No.				
53.Suitable Arc welding tablewith positioner6 Nos.54.Trolley for cylinder (H.P. Unit)2 Nos.55.Hand shearing machine capacitycut 6 mm sheets and flats1 No.56.Power saw machine18" or blade size 450 mm1 No.57.Portable drilling machine(Cap. 6 mm)1 No.58.Oven, electrode drying0 to 350°C, 10 kg capacity, depth 450mm to 500 mm, intake capacity 10 kg1 No.59.Work bench340x120x75 cm with 4 bench vices of 150 mm jaw opening4 sets60.Oxy Acetylene Gas cutting blow pipe2 sets61.Oxygen, Acetylene Cylinders **2 each62.CO2 cylinder **2 Nos.63.Argon gas cylinder **2 Nos.64.Anvil 24 sq. inches working area with stand1 No.65.Swage block 5048Cast iron 16x16x16 inch1 No.66.Magnetic particle testing Kit #1 set67.Fire extinguishers (foam type and CO2type)1. No.68.Fire buckets with stand4 Nos.69.Portable abrasive cut-off machine1 No.				
54.Trolley for cylinder (H.P. Unit)2 Nos.55.Hand shearing machine capacitycut 6 mm sheets and flats1 No.56.Power saw machine18" or blade size 450 mm1 No.57.Portable drilling machine(Cap. 6 mm)1 No.0ven, electrode drying0 to 350°C, 10 kg capacity, depth 450mm to 500 mm,intake capacity 10 kg1 No.59.Work bench340x120x75 cm with 4 bench vices of 150 mm jaw opening4 sets jaw opening60.Oxy Acetylene Gas cutting blow pipe2 sets61.Oxygen, Acetylene Cylinders **2 each62.CO2 cylinder **2 Nos.63.Argon gas cylinder **2 Nos.64.Anvil 24 sq. inches working area with stand1 No.65.Swage block 5048Cast iron 16x16x16 inch1 No.66.Magnetic particle testing Kit #1 set67.Fire extinguishers (foam type and CO2type)1. No.68.Fire buckets with stand4 Nos.69.Portable abrasive cut-off machine1 No.				
S5. Hand shearing machine capacity  S6. Power saw machine  S7. Portable drilling machine  Oven, electrode drying  S8. Over, electrode drying  S9. Work bench  S9. Over, electrode Gas cutting blow pipe  S9. Work bench  S9. Over, electrode Gas cutting blow pipe  S9. Over, electrode drying  S9. Work bench  S9. Work bench  S9. Over, electrode drying  S9. Work bench  S9. Over, electrode drying  S9. Over, elec			with positioner	
55. Hand shearing machine capacity  56. Power saw machine  57. Portable drilling machine  Oven, electrode drying  58.  Work bench  59. Work bench  50. Oxy Acetylene Gas cutting blow pipe  60. Oxygen, Acetylene Cylinders **  61. Oxygen, Acetylene Cylinders **  62. CO2 cylinder **  63. Argon gas cylinder **  64. Anvil 24 sq. inches working area with stand  65. Swage block 5048  66. Magnetic particle testing Kit #  67. Fire extinguishers (foam type and CO2type)  68. Fire buckets with stand  69. Portable abrasive cut-off machine	54.	Trolley for cylinder (H.P. Unit)		
56.Power saw machine18" or blade size 450 mm1 No.57.Portable drilling machine(Cap. 6 mm)1 No.Oven, electrode drying0 to 350°C, 10 kg capacity, depth 450mm to 500 mm,intake capacity 10 kg1 No.58.340x120x75 cm with 4 bench vices of 150 mm jaw opening4 sets jaw opening60.Oxy Acetylene Gas cutting blow pipe2 sets61.Oxygen, Acetylene Cylinders **2 each62.CO2 cylinder **2 Nos.63.Argon gas cylinder **2 Nos.64.Anvil 24 sq. inches working area with stand1 No.65.Swage block 5048Cast iron 16x16x16 inch1 No.66.Magnetic particle testing Kit #1 set67.Fire extinguishers (foam type and CO2type)1. No.68.Fire buckets with stand4 Nos.69.Portable abrasive cut-off machine1 No.	55.	Hand shearing machine capacity		1 No.
57. Portable drilling machine  Oven, electrode drying  I No.	56.	Power saw machine		1 No.
Oven, electrode drying  0 to 350°C, 10 kg capacity, depth 450mm to 500 mm,intake capacity 10 kg  340x120x75 cm with 4 bench vices of 150 mm jaw opening  60. Oxy Acetylene Gas cutting blow pipe 61. Oxygen, Acetylene Cylinders ** 62. CO2 cylinder ** 63. Argon gas cylinder ** 64. Anvil 24 sq. inches working area with stand 65. Swage block 5048 66. Magnetic particle testing Kit # 67. Fire extinguishers (foam type and CO2type)  68. Fire buckets with stand 69. Portable abrasive cut-off machine  1 No.  1 No.  1 No.  2 Nos. 2 Nos. 2 Nos. 2 Nos. 2 Nos. 4 Nos. 4 Nos. 4 Nos.		Portable drilling machine	(Cap. 6 mm)	
58. Capacity, depth 450mm to 500 mm, intake capacity 10 kg  59. Work bench S4 S40x120x75 cm with 4 bench vices of 150 mm jaw opening  60. Oxy Acetylene Gas cutting blow pipe  61. Oxygen, Acetylene Cylinders **  62. CO2 cylinder **  63. Argon gas cylinder **  64. Anvil 24 sq. inches working area with stand  65. Swage block 5048  66. Magnetic particle testing Kit #  67. Fire extinguishers (foam type and CO2type)  68. Fire buckets with stand  69. Portable abrasive cut-off machine				
to 500 mm,intake capacity 10 kg  340x120x75 cm with 4 bench vices of 150 mm jaw opening  60. Oxy Acetylene Gas cutting blow pipe 61. Oxygen, Acetylene Cylinders ** 62. CO2 cylinder ** 63. Argon gas cylinder ** 64. Anvil 24 sq. inches working area with stand 65. Swage block 5048 66. Magnetic particle testing Kit # 67. Fire extinguishers (foam type and CO2type) 68. Fire buckets with stand 69. Portable abrasive cut-off machine  340x120x75 cm with 4 bench vices of 150 mm 4 sets 2 sets 2 each 2 each 2 Nos. 2 Nos. 2 Nos. 2 Nos. 4 No. 4 Nos.			capacity, depth 450mm	
59.Work bench340x120x75 cm with 4 bench vices of 150 mm jaw opening60.Oxy Acetylene Gas cutting blow pipe2 sets61.Oxygen, Acetylene Cylinders **2 each62.CO2 cylinder **2 Nos.63.Argon gas cylinder **2 Nos.64.Anvil 24 sq. inches working area with stand1 No.65.Swage block 5048Cast iron 16x16x16 inch1 No.66.Magnetic particle testing Kit #1 set67.Fire extinguishers (foam type and CO2type)1. No.68.Fire buckets with stand4 Nos.69.Portable abrasive cut-off machine1 No.	58.		to 500 mm,intake	
59.Work benchbench vices of 150 mm jaw opening4 sets60.Oxy Acetylene Gas cutting blow pipe2 sets61.Oxygen, Acetylene Cylinders **2 each62.CO2 cylinder **2 Nos.63.Argon gas cylinder **2 Nos.64.Anvil 24 sq. inches working area with stand1 No.65.Swage block 5048Cast iron 16x16x16 inch1 No.66.Magnetic particle testing Kit #1 set67.Fire extinguishers (foam type and CO2type)1. No.68.Fire buckets with stand4 Nos.69.Portable abrasive cut-off machine1 No.			capacity 10 kg	
jaw opening   2 sets			340x120x75 cm with 4	
<ul> <li>60. Oxy Acetylene Gas cutting blow pipe</li> <li>61. Oxygen, Acetylene Cylinders **</li> <li>62. CO₂ cylinder **</li> <li>63. Argon gas cylinder **</li> <li>64. Anvil 24 sq. inches working area with stand</li> <li>65. Swage block 5048</li> <li>66. Magnetic particle testing Kit #</li> <li>67. Fire extinguishers (foam type and CO₂type)</li> <li>68. Fire buckets with stand</li> <li>69. Portable abrasive cut-off machine</li> <li>2 sets</li> <li>2 Nos.</li> <li>1 No.</li> <li>4 Nos.</li> <li>1 No.</li> </ul>	59.	Work bench	bench vices of 150 mm	4 sets
61.Oxygen, Acetylene Cylinders **2 each62.CO2 cylinder **2 Nos.63.Argon gas cylinder **2 Nos.64.Anvil 24 sq. inches working area with stand1 No.65.Swage block 5048Cast iron 16x16x16 inch1 No.66.Magnetic particle testing Kit #1 set67.Fire extinguishers (foam type and CO2type)1. No.68.Fire buckets with stand4 Nos.69.Portable abrasive cut-off machine1 No.			jaw opening	
$\begin{array}{cccccccccccccccccccccccccccccccccccc$	60.	Oxy Acetylene Gas cutting blow pipe		2 sets
63.Argon gas cylinder **2 Nos.64.Anvil 24 sq. inches working area with stand1 No.65.Swage block 5048Cast iron 16x16x16 inch1 No.66.Magnetic particle testing Kit #1 set67.Fire extinguishers (foam type and CO2type)1. No.68.Fire buckets with stand4 Nos.69.Portable abrasive cut-off machine1 No.	61.			2 each
64. Anvil 24 sq. inches working area with stand  65. Swage block 5048  66. Magnetic particle testing Kit #  67. Fire extinguishers (foam type and CO₂type)  68. Fire buckets with stand  69. Portable abrasive cut-off machine		•		
64.standCast iron 16x16x16 inch1 No.65.Swage block 5048Cast iron 16x16x16 inch1 No.66.Magnetic particle testing Kit #1 set67.Fire extinguishers (foam type and CO2type)1. No.68.Fire buckets with stand4 Nos.69.Portable abrasive cut-off machine1 No.	63.	,		
66.Magnetic particle testing Kit #1 set67.Fire extinguishers (foam type and CO2type)1. No.68.Fire buckets with stand4 Nos.69.Portable abrasive cut-off machine1 No.	64.			1 No.
66.Magnetic particle testing Kit #1 set67.Fire extinguishers (foam type and CO2type)1. No.68.Fire buckets with stand4 Nos.69.Portable abrasive cut-off machine1 No.	65.	Swage block 5048	Cast iron 16x16x16 inch	1 No.
67. CO <sub>2</sub> type)  68. Fire buckets with stand  69. Portable abrasive cut-off machine  1 No.	66.	Magnetic particle testing Kit #		1 set
68. Fire buckets with stand 4 Nos. 69. Portable abrasive cut-off machine 1 No.	67.	, ,,		1. No.
69. Portable abrasive cut-off machine 1 No.	68.	,, ,		4 Nos.
71. Welding Simulators for 1 each				



	SMAW/GTAW/GMAW		(Optional)
	Water cooled induction welding/	200-250 Amp., induction	1
72.	Brazing machine	coil length 3 inch and 2.5	
		inch	
	Plastic welding machine with hot air	temp. display, variable	1
73.	gun	temp., PE,PP& PVC sheet	
/3.		or pipe welding control	
		with stand. Accessories.	
74.	Swaging and flooring tool kit 45°	1/8 to ¾ inch	
/4.	tubing		
C. CON	ISUMABLE		
75.	Leather Hand Gloves	14"	20 pairs
76.	Cotton hand Gloves	8"	20 pairs
77.	Leather Apron leather		20 Nos.
78.	S.S Wire brush	5 rows and 3 rows	20 Nos. each
79.	Leather hand sleeves	16"	20 pairs
80.	Safety boots for welders	Size 7,8,9,10	20pairs
81.	Leg guards leather		20pairs
82.	Rubber hose clips	1/2"	20 Nos.
0.2	Rubber hose oxygen	8 mm dia X 10 Mtr. long	2 Nos.
83.		as per BIS	
84.	Rubber hose acetylene	8 mm dia X 10 Mtr. long	2 Nos.
04.		as per BIS	
85.	Arc welding cables multi cored	400/ 600 amp as per BIS	45 mts. each
85.	copper		
86.	Arc welding single coloured glasses	108 mm x 82 mm x 3 mm.	34 Nos.
- 50.		DIN 11A &12 A	
87.	Arc welding plain glass	108 mm x 82 mm x 3 mm.	68 Nos.
88.	Gas welding Goggles	with Colour glass 3 or 4A	34 Nos.
00.		DIN	
89.	Safety goggles plain		34 Nos.
90.	Spark lighter	CUP lighter for welding	6 Nos.
91.	AG 4 Grinding wheels		50 Nos.
92.	Earth clamp	600A	6 Nos.
93.	Electrode holder	600 amps	6 Nos.
94.	Die penetrant testing kit		1 set
95.	Anti spatter spray can	100 to 300 ml	5 Nos.
96.	GMAW Torch nozzle tip	Size 0.8, 1.0, 1.2 (in mm)	5 Nos. each
97.	TIG welding torch ceramic nozzle	Size 3,4,5,6,8	4 Nos. each
98.	Tungsten electrode	1.0, 1.6, 2.0 (in mm),	5 Nos. each
<i>J</i> 0.		length 150 mm	
99.	Brass filler wire	1.0mm, 2.0 mm	



100.	AG4 cutting wheels		100 Nos.	
101.	CCMS filler wire 1.0 mm		4 Kg	
102.	Brass filler wire	1.0 mm	4 Kg	
103.	Copper filler wire	1.0 mm	4 Kg	
104.	Flux for Brass		500 Gram	
105.	Flux for Copper		500 Gram	
D. CLA	D. CLASS ROOM FURNITURE FOR TRADE THEORY			
106.	Instructor's table and Chair (Steel)		1 set	
107.	Students chairs with writing pads		20 Nos.	
108.	White board size 1200mm X 900 mm		1 No.	
109.	Instructor's laptop with latestconfiguration pre-loaded with operating system and MS Office package.		1No.	
110.	LCD projector with screen.		1No.	
111.	<ol> <li>Welding Process, Inspection&amp; codes DVD/ CDs.</li> </ol>		1 set each (optional)	

## Note:

- 1. \*\* Optionally Gas cylinders can also be hired as and when required.
- 2. # One machine per institute irrespective of number of units of welding trade is necessary.



## **ABBREVIATIONS**

_	T
CTS	Craftsmen Training Scheme
ATS	Apprenticeship Training Scheme
CITS	Craft Instructor Training Scheme
DGT	Directorate General of Training
MSDE	Ministry of Skill Development and Entrepreneurship
NTC	National Trade Certificate
NAC	National Apprentice Certificate
NCIC	National Craft Instructor Certificate
LD	Locomotor Disability
СР	Cerebral Palsy
MD	Multiple Disabilities
LV	Low Vision
НН	Hard of Hearing
ID	Intellectual Disabilities
LC	Leprosy Cured
SLD	Specific Learning Disabilities
DW	Dwarfism
MI	Mental Illness
AA	Acid Attack
PwD	Person with disabilities
SMAW	Shielded Metal Arc Welding
OAW	Oxy-Acetylene Gas Welding
OAG C	Oxy-Acetylene Gas Cutting
GMAW	Gas Metal Arc Welding
GTAW	Gas Tungsten Arc Welding
PAC	Plasma Arc Cutting
RW	Resistance Welding
OAW	Oxy-Acetylene Gas Welding
OAG C	Oxy-Acetylene Gas Cutting



I&T	Inspection & Testing
WT	Wall Thickness.
PP	Polypropylene
PE	Polyethylene
PVC	Polyvinylchloride

